

CLAIMS

1. A cement setting accelerator comprising calcium hydroxide particles having an average particle diameter of 3 μm or less.
5
2. The cement setting accelerator according to claim 1 which is in the form of a slurry.
3. A cement composition comprising 100 parts by weight
10 of a cement and 0.05 to 10 parts by weight of calcium hydroxide as the cement setting accelerator of claim 1 or 2.
4. A process for manufacturing a cement composition comprising adding a water slurry of calcium hydroxide
15 particles having an average particle diameter of 3 μm or less to a cement.
5. Use of calcium hydroxide particles having an average
20 particle diameter of 3 μm or less as a cement setting accelerator.